

DOGAMIN NATURAL

Mineral-Based Natural Coating

DOGAMIN NATURAL is a decorative, mineral coating material containing naturally colored stones. Produced in two different grain sizes: 1 mm and 3 mm.



The thick film layer formed during application covers surface defects.

High resistance to UV, alkali, and color fading.

Resistant to exterior weather conditions; unaffected by rain, snow, humidity, extreme heat, or cold.

Due to its water vapor permeability, it allows vapor to escape and the surface to breathe.

Water-based, environmentally friendly, and harmless to human health.

CONTENT: Acrylic-based – water-based	PACKAGING: 25 KG
THINNING: 5% clean water	DRYING TIME: <i>Drying Time Touch dry (at 23°C): 4-6 hours</i> <small>*drying time may be longer at higher relative humidity and lower temperature.</small>
PRIMER: San Deco Uniprimer	Fully Dry: 24-48 hours
APPLICATION TOOL: Trowel	COLORING: Vision, RAL, NCS
NUMBER of COATS: 1	VOC: EU Directive 2004/42/EC – Category A/I: Decorative effect coatings (water-based): 200 g/L (2010) DOGAMIN NATURAL contains a maximum of 40 g/L VOC
STORAGE and SHELF LIFE: <i>Can be stored for 2 years in its unopened original package, in a cool and dry place, protected from direct sunlight, between +5°C and +35°C.</i>	

CONSUMPTION - Single Coat : Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.



Dogamin 1 mm:
With 1 L, 0.75-0.85 m² can be covered.
With 1 kg, 0.4-0.45 m² can be covered.
For 1 m² surface: 1175-1330 ml or 2220-2500 g required.

Dogamin 3 mm:
With 1 L, 0.5-0.6 m² can be covered.
With 1 kg, 0.25-0.35 m² can be covered.
For 1 m² surface: 1660-2000 ml or 3000-3800 g required.

APPLICATION AREA

Used on all types of exterior wall surfaces such as traditional plaster, fair-faced concrete, cement boards, and thermal insulation systems, together with the appropriate primer.

SURFACE PREPARATION

All dirt, oil, loose paint, and dust must be removed from the surface before application.

Surface defects should be repaired using San Deco Acrylic Putty Thick, and then primed with San Deco Uniprimer.

It is recommended to use a primer tinted in the same color as the selected topcoat.

SURFACE CONDITIONS

During application and until full drying, the ambient and surface temperature should be between +5°C and +35°C.

Do not apply under direct sunlight.

The surfaces to be painted must be completely dry.

Ambient humidity should be below 75%.
Surface moisture content should be below 10%.

APPLICATION

Before application, Dogamin Natural should be diluted with 5% clean water and mixed thoroughly until homogeneous.

Apply one uniform coat over the entire surface using a trowel.

Approximately 20 minutes after application, the surface should be smoothed with a steel trowel.

When using multiple batch numbers within the same project, it is recommended to mix batches evenly prior to application to avoid batch-to-batch color or texture variation.

HAZARD & PRECAUTIONARY STATEMENTS

H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapours/spray.
P333 + P313: If skin irritation or rash occurs: Get medical advice/attention.
P362 + P364: Take off contaminated clothing and wash before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, please refer to the product's Safety Data Sheet (SDS).

This technical data sheet has been prepared based on laboratory data obtained under normal conditions. For details not included above, please consult technical staff. The manufacturer assumes no responsibility for errors arising from insufficient information. The right to amend this document is reserved by the company. For detailed information about health, safety, and transportation risks and precautions, please refer to the Material Safety Data Sheet (MSDS).

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified under ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.