

RULOTEX

Matte Textured Elastomeric Exterior Coating

RULOTEX is a matte textured exterior wall paint.



Thanks to its elastic structure, it bridges cracks on the applied surface and resists cracks that may occur due to building settlement.

High resistance to color fading and alkalis.


Resistant to exterior conditions such as rain, snow, humidity, and extreme heat or cold.


Thanks to its water vapor permeability, it allows vapor to escape and the surface to breathe.


Water-based, environmentally friendly, and safe for human health.


 **CONTENT:** Acrylic-based - water-based

 **PACKAGING:** 15 L


 **THINNING:** With a maximum of 5-10% clean water by volume.

 **DRYING TIME:** Drying Time Touch dry (at 23°C): 4-5 hours
**drying time may be longer at higher relative humidity and lower temperature.*


 **PRIMER:** Uniprimer or Rulotex diluted 30% by volume


 **Fully Dry:** 24 hours

 **APPLICATION TOOL:** Roller, brush, spray

 **COLORING:** Vision, RAL, NCS

 **NUMBER of COATS:** 1

 **STORAGE and SHELF LIFE:**
Can be stored for 2 years between +5°C and +35°C in its unopened packaging, in a cool and dry place, protected from direct sunlight.

 **VOC:**
EU limit value (Directive 2004/42/EC)
Category A/C: Exterior walls of mineral substrates (water-based): 40 g/l (2010)
RULOTEX: Contains a maximum of 18 g/l VOC

CONSUMPTION - Single Coat : Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.



With 1 L: 1.25-2 m² coverage

With 1 kg: 0.85-1.35 m² coverage

Paint consumption per m²: 500-800 ml or 750-1200 g.

APPLICATION AREA

Can be used with a suitable primer on exterior surfaces such as plaster, exposed concrete, and cement boards of all types of buildings, and also for decorative purposes on interior surfaces if desired.

SURFACE PRAPARATION

All dirt, oil, blistered paints, and dust must be cleaned from the surfaces before application.

Surface defects should be repaired with San Deco Acrylic Putty Thick.

The surface can be prepared with San Deco Uniprimer tinted in the selected façade color, or for better results, Rulotex diluted 30% by volume can be used as a primer alternative.

SURFACE CONDITIONS

During application and until the products are completely dry, the ambient and surface temperature should be at least +5°C and at most +35°C.

Do not apply under direct sunlight.

The surfaces to be painted must be completely dry.

Ambient humidity should be below 75% during application.

Surface moisture content should be below 10%.

APPLICATION

Rulotex should be thinned with a maximum of 5-10% clean water by volume and mixed homogeneously before application.

Apply to the surface in a single coat using a roller, brush, or spray method.

For thicker textured applications, the product should be applied without dilution.

If multiple batch numbers are used in the same project, mix them in equal proportions before application to avoid batch-based differences.

HAZARD & PRECAUTIONARY STATEMENTS AND EXPLANATIONS

H317: May cause an allergic skin reaction.

P261: Avoid breathing dust/fume/gas/mist/vapors/spray.

P333+P313: If skin irritation or rash occurs: Get medical advice/attention.

P362+P364: Take off contaminated clothing and wash before reuse.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P321: Specific treatment required (see label).

P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, refer to the product's Safety Data Sheet (SDS).

This technical data sheet is based on laboratory data under normal conditions. For details not covered above, consult technical staff. The manufacturer cannot be held responsible for errors arising from insufficient information. The right to modify this information is reserved. For detailed information regarding health, safety, transport risks, and precautions, refer to the Material Safety Data Sheet.

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified for ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.