

TRAVERTEX

Exterior Coating with Linear Texture

TRAVERTEX is a line-textured, decorative exterior coating material.



The thick film layer formed during application conceals surface imperfections.

It has high resistance to UV rays, alkali, and color fading.

Resistant to outdoor conditions such as rain, snow, humidity, and extreme heat or cold.

Its water vapor permeability allows vapor to escape, enabling the surface to breathe.

More elastic compared to cement-based products, allowing it to bridge minor cracks on the surface.

Unaffected by cracks caused by building settlement.

Water-based, environmentally friendly, and safe for human health.

 CONTENT: Acrylic-based - water-based	 PACKAGING: 25 KG
 THINNING: Ready to use, do not dilute.	 DRYING TIME: Drying Time Touch dry (at 23°C): 4-6 hours <small>*drying time may be longer at higher relative humidity and lower temperature.</small>
 PRIMER: San Deco Uniprimer	 Fully Dry: 24-48 hours
 APPLICATION TOOL: Trowel	 COLORING: NCS, RAL
 NUMBER of COATS: 1	 VOC: EU Limit Value (Directive 2004/42/EC) Category A/I: Decorative effect coatings (water-based): 200 g/L (2010) TRAVERTEX contains a maximum of 37.8 g/L VOC.
 STORAGE and SHELF LIFE: Can be stored for 2 years in its unopened original package, in a cool and dry place, protected from direct sunlight, between +5 °C and +35 °C.	

CONSUMPTION - Single Coat : Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.



1 L covers 0.5-0.6 m²

1 kg covers 0.3-0.4 m²

Material consumption for 1 m² surface:

1685-1965 ml and 2500-3500 g.

APPLICATION AREA

Used as a coating material on the exterior surfaces of all types of buildings, over rough plaster, fair-faced concrete, cement board, and thermal insulation systems, together with a suitable primer.

SURFACE PREPARATION

All dirt, oil, blistered paint, and dust should be cleaned from the surface. Surface imperfections should be repaired using San Deco Acrylic Putty Thick, followed by priming with San Deco Uniprimer.

It is recommended to use a primer in the same color as the selected facade color.

SURFACE CONDITIONS

During application and until complete drying, ambient and surface temperature should be between +5°C and +35°C.

Do not apply under direct sunlight.

The surface to be painted must be completely dry.

Ambient humidity should be below 75%.

Surface moisture content should be below 10%.

APPLICATION

TRAVERTEX should be mixed thoroughly before application without dilution.

Apply one coat using a trowel. The application thickness should be adjusted according to the coarsest grain size in the product.

Create a vertical line texture using a plastic trowel.

If multiple production batches are used within the same project, mix them in equal proportions before application to avoid color or texture differences.

HAZARD & PRECAUTIONARY STATEMENTS

H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapors/spray.
P333 + P313: If skin irritation or rash occurs: Get medical advice/attention.
P362 + P364: Take off contaminated clothing and wash it before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more detailed information, refer to the product's Safety Data Sheet (SDS).

This technical data sheet is prepared based on laboratory data under standard conditions. For details not sufficiently covered above, please consult technical personnel. The manufacturer is not responsible for errors arising from insufficient information. The right to make changes to this information is reserved by our company. For detailed information regarding product health, safety, transport risks, and precautions, refer to the Material Safety Data Sheet (MSDS).

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified under ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.