

# DECOSTUCCO

## *Glossy Venetian Plaster with Marble Effect*

DECOSTUCCO is a paste-form, glossy Venetian plaster containing quartz limestone, developed for interior spaces to create a shiny marble effect.



*Its high gloss makes colors vivid and bright.*

*It is water-based, environmentally friendly, and harmless to human health.*

 <b>CONTENT:</b> Acrylic-based - water-based	 <b>PACKAGING:</b> 4 KG ; 10 KG ; 20 KG
 <b>THINNING:</b> Ready to use, do not dilute.	 <b>DRYING TIME:</b> Drying Time Touch dry (at 23 °C): 2-3 hours <small>*drying time may be longer at higher relative humidity and lower temperature.</small>
 <b>PRIMER:</b> San Deco Decoprimer	 <b>Fully Dry:</b> 24 hours
 <b>APPLICATION TOOL:</b> Trowel, polishing machine, spatula	 <b>COLORING:</b> Decostucco Color Chart, Liberte Art
 <b>NUMBER of COATS:</b> 2	
 <b>STORAGE and SHELF LIFE:</b> Can be stored unopened for 2 years between +5 °C and +35 °C, in a cool and dry place protected from direct sunlight.	 <b>VOC:</b> EU Limit Value (Directive 2004/42/EC) Category A/I: Decorative effect coatings (water-based): 200 g/L (2010) DECOSTUCCO: contains a maximum of 48.6 g/L VOC

**CONSUMPTION** - Three Coats : Consumption may vary depending on the type, absorbency, and structure of the surface, as well as application techniques. For precise consumption, a controlled sample application should be performed.



1 L covers 3,8-4,7 m<sup>2</sup>,  
1 kg covers 2,3-2,9 m<sup>2</sup>.

Paint consumption per 1 m<sup>2</sup>: 210-260 ml and 340-430 g.

## APPLICATION AREA

Should be used with its own primer after proper surface preparation on interior walls, plaster, exposed concrete, and wooden surfaces.

## SURFACE PREPARATION

After removing any dirt, oil, loose paint, and dust from the surfaces to be applied, surface defects should be repaired with San Deco Acrylic Putty Fine, and then primed with San Deco Decoprimer.

## SURFACE CONDITIONS

During application and until full drying, ambient and surface temperature should be minimum +5°C and maximum +35°C.

Ambient humidity should be below 75% during application.

Surface moisture content should be below 10% before application.

## APPLICATION

Decostucco should be mixed homogeneously without dilution before application.

Apply one coat to the surface with a steel trowel and allow to dry for about 6-8 hours. After drying, apply the second coat.

After 24 hours of drying, sand the surface lightly with fine sandpaper. As a third coat, apply the desired effect using a spatula or trowel. Before the surface is completely dry, press and polish it with a steel trowel. For a glossier finish, the use of Sandeco Wax is recommended.

For more detailed application information, product application videos can be watched.

If multiple batch numbers are used in the same project, to prevent batch-based differences, mix the batches in equal proportion before application.

Local retouching is not recommended. For repair operations, it is recommended to reapply the entire damaged surface.

## HAZARD & PRECAUTIONARY STATEMENTS AND EXPLANATIONS

H317: May cause an allergic skin reaction.  
P261: Avoid breathing dust/fume/gas/mist/vapors/spray.  
P333+P313: If skin irritation or rash occurs: Get medical advice/attention.  
P362+P364: Take off contaminated clothing and wash before reuse.  
P280: Wear protective gloves/protective clothing/eye protection/face protection.  
P321: Specific treatment required (see label).  
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, please refer to the product's Safety Data Sheet (SDS).

This technical data sheet is prepared based on laboratory data under normal conditions. For details not sufficiently covered above, please consult technical personnel. The manufacturer is not responsible for errors resulting from lack of information. The company reserves the right to modify this information. For detailed information about product health, safety, transport risks, and precautions, refer to the Material Safety Data Sheet.

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., which holds conformity certificates for ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.