

DENPLAS

Plastic Water-Based Matte Interior Paint












DENPLAS is a matte decorative topcoat paint developed for interior surfaces.



Washable surface.

High coverage.

Water-based, environmentally and human-health friendly.

 CONTENT: <i>Acrylic-based – water-based</i>	 PACKAGING: 2,5 L ; 7,5 L ; 13,5 L ; 15 L
 THINNING: <i>Max. 15% with clean water</i>	 DRYING TIME: <i>Drying Time Touch dry (at 23°C): 4-6.5 hours</i> <small>*drying time may be longer at higher relative humidity and lower temperature.</small>
 PRIMER: <i>San Deco Uniprimer</i>	 Fully Dry: 24 hours
 APPLICATION TOOL: <i>Roller, brush, spray</i>	 COLORING: <i>Vision, RAL, NCS</i>
 NUMBER of COATS: 2	 VOC: <i>Limit value EU (Directive 2004/42/EC)</i> <i>Category A/a: Interior wall and ceiling paints (water-based): 30 g/l (2010) DENPLAS: contains max. 24.2 g/l VOC</i>
 STORAGE and SHELF LIFE: <i>Can be stored for 2 years in its unopened original packaging at +5°C to +35°C in a cool, dry place away from direct sunlight.</i>	

CONSUMPTION - Single Coat : *Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.*



1 L covers 11.5–15 m²,
1 kg covers 7.5–9 m².
Paint consumption per m²: 70–85 ml or 110–135 g.

APPLICATION AREA

Applied together with its suitable primer on properly prepared mineral surfaces such as plaster, concrete, cement board, gypsum panel, and previously painted interior surfaces.

SURFACE PREPARATION

All kinds of dirt, oil, loose or blistered paints, and dust must be removed from the surface before application. Surface imperfections should be repaired with San Deco Acrylic Putty Fine, then primed with San Deco Uniprimer.

It is recommended to use a primer of the same color as the selected paint color.

SURFACE CONDITIONS

Ambient and surface temperature should be between +5°C and +35°C during application and drying.

Ambient humidity should be below 75%.

Surface humidity should be below 10%.

APPLICATION

Before application, DENPLAS should be diluted up to 15% with clean water by volume and mixed until homogeneous.

Apply two (2) coats using a roller, brush, or spray gun. Wait at least 4 hours between coats.

If multiple batch numbers are to be used in the same project, it is recommended to mix them together to avoid tonal differences.

HAZARD & PRECAUTIONARY STATEMENTS

- H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapors/spray.
P333+P313: If skin irritation or rash occurs: Get medical advice/attention.
P362+P364: Take off contaminated clothing and wash it before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, refer to the product's Safety Data Sheet (SDS).



Complies with TS 5808/2012.



Complies with the G regulation.

This technical data sheet is prepared based on laboratory data under standard conditions. For further details not covered above, please consult technical staff. The manufacturer shall not be held responsible for any errors resulting from insufficient information. The company reserves the right to change the details in this document. For detailed information regarding health, safety, and transport risks and precautions, please refer to the Material Safety Data Sheet (MSDS).

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified to ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.