

APPLICATION AREA

Applied over Mirzasto used on interior surfaces.

SURFACE PREPARATION

All dirt, oil, loose/peeling paints, and dust must be removed from the application surface. Surface defects should be corrected with San Deco Acrylic Putty Fine, then primed with San Deco Decoprimer, and Mirzasto application should already be completed.

SURFACE CONDITIONS

During application and until full drying is completed, the ambient and surface temperature must be between +5°C and +35°C.

Ambient humidity must be below 75%.

Surface moisture content must be below 10%.

APPLICATION

Effect Finish should be applied without thinning, after mixing thoroughly, onto surfaces where Mirzasto application has been completed.

Approximately 4-5 hours after the Mirzasto application—once the surface is fully dry—Effect Finish is applied.

According to the color selected from the color chart, the first Effect Finish color is applied with a trowel.

After waiting 2-3 hours, the second Effect Finish color is applied with a trowel to achieve the desired effect.

Excess product must be removed with the trowel. For more detailed information, product application videos may be viewed.

If more than one batch is used in the same project, mix the batches in equal proportions prior to application to prevent batch-based differences.

Local touch-up is not recommended. In case of repair, re-application to the entire damaged area is advised.

HAZARD & PRECAUTIONARY STATEMENTS

- H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapours/spray.
P333 + P313: If skin irritation or rash occurs: Get medical advice/attention.
P362 + P364: Take off contaminated clothing and wash it before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment required (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, refer to the product Safety Data Sheet (SDS).

This technical data sheet is prepared based on laboratory results under normal conditions. Consult technical personnel for details not covered above. The manufacturer is not responsible for any errors resulting from insufficient information. The right to revise this document is reserved by our company. For detailed information on product health-safety-transport hazards and precautions, refer to the Material Safety Data Sheet.

Produced by Deko Boya Sanayi ve Tic. A.Ş., certified with ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 systems.