



## Exterior Products Range

# Rulotex

### DESCRIPTION

RULOTEX is an acrylic emulsion based, long life decorative final coat exterior paint.

### APPLICATION AREA

RULOTEX can be used on the siding of all kinds of buildings, surfaces like rough cast, exposed concrete and cement sheets and in interior surfaces with suitable coat for decoration.

### FEATURES

- Elastic, retains its elasticity even in low temperatures, and serves as a bridge fort he cracks forming on the surface,
- Not affected by the cracks forming due to buildings settling,
- Provides complete protection against exterior weather conditions on its application surface, and also prevents forming of mould and fungus,
- Due its high vapor permeability, it allows surface to discharge the steam and breathe,
- UV resistant, no colour fades,
- High alkaline resistance,
- As it is water-based, it is harmless to human health and environment,

### SURFACE PREPARATION

- Clean all dirt, oil, blistered paint and dust off the application surface; level the surface defects with SAN DECO ACRYLIC PUTTY EXTERIOR
- Before going on application, prepare the surface with SAN DECO UNIPRIMER undercoat by using the same color of undercoat as the selected color or for a better result RULOTEX can be diluted 30% and used as an undercoat.

### APPLICATION INSTRUCTIONS

- RULOTEX is diluted with 5-10% water; it should be applied with a roll, brush or spraying method as one layer.
- If an application with thick pattern is preferred, the product shall be applied undiluted,
- The environment of application must be kept between +5°C to +35°C within 24 hours during and after the application.

### DRYING TIME

Allow 4-6 hours for touch dry and 24 hours for complete dry at 23°C environment conditions.

### THEORETICAL CONSUMPTION

Depending on surface smoothness, porosity and application methods, for a single coat application;

-1 lt covers 1,25– 2,0 m<sup>2</sup> of surface,

-1 kg covers 0,85 – 1,35 m<sup>2</sup> of surface,

-The paint consumption for 1 m<sup>2</sup> area is 500 -800 ml and 750 - 1200 gr.

### STORAGE

It should be stored in a sealed package, in a cool and dry place and protected from direct sunlight; and at a temperature between +5°C and +35°C.

### DEKA BOYA SANAYİ ve TİC. A.Ş.



## Exterior Products Range

# Rulotex

### HAZARD STATEMENTS

**H317** May cause an allergic skin reaction.

**H362** May cause harm to breast-fed children

### PRECAUTIONARY STATEMENTS

**P261** Avoid breathing dust/fume/gas/mist/vapours/spray.

**P263** Avoid contact during pregnancy/while nursing,

**P280** Wear protective gloves/protective clothing/eye protection/face protection.

**P301+P310** IF SWALLOWED: Immediately call a POISON CENTER (114) or doctor/physician.

**P302 + P352** IF ON SKIN: Wash with plenty of soap and water.

**P333 + P313** If skin irritation or rash occurs: Get medical advice/attention.

**P501** Dispose of contents/container in accordance with local/regional/national/international regulation.

**EUH208** Contains chloromethylisothiazolinone and methylisothiazolinone (3:1)

May produce an allergic reaction.

Note: For more information, please check the Safety Data Sheet (SDS) of the product

#### Product Technical Data Sheet No. EP.006.ENG - Rev00 March 2020

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical staff for details that are not sufficient above. Otherwise, errors that will occur as a result of insufficient information do not impose responsibility on the manufacturer. Deka Boya San. ve Tic. A.S. reserves the right to change this information. If necessary, you can find detailed information about the health-safety-transportation risks and precautions of the products from the Material Safety Data Sheet.

**This product is produced by Deka Boya Sanayi ve Tic. A.S. who is also certified by the standarts of ISO 9001, ISO 14001, ISO 45001.**

#### DEKA BOYA SANAYİ ve TİC. A.Ş.

Merkez: Yukarı Dudullu Mah. Necip Fazıl Bulvarı Keyap Çarşısı D2 Blok No:61 Ümraniye/İstanbul Tel: +90 (216) 575 56 56  
Fabrika: S.S. İstanbul Memerciler Küçük Sanayi Sitesi 34.Cd. No:3 Dilovası/Kocaeli Tel: +90 (262) 728 10 88