

# WAX












## Gloss-Enhancing Decostucco Polish

WAX is a topcoat polish that provides a glossy marble-like appearance to the Decostucco product.



*Easy to apply.*

*It is water-based, friendly to human health and the environment.*

 <b>CONTENT:</b> <i>Water-based wax</i>	 <b>PACKAGING:</b> 0,5 KG
 <b>THINNING:</b> <i>Ready to use, does not require thinning.</i>	 <b>DRYING TIME:</b> <i>Drying Time Touch dry (at 23°C): 30-60 minutes</i> <i>*drying time may be longer at higher relative humidity and lower temperature.</i>
 <b>PRIMER:</b> -	 <b>Fully Dry:</b> 24 hours
 <b>APPLICATION TOOL:</b> <i>Trowel</i>	 <b>COLORING:</b> -
 <b>NUMBER of COATS:</b> 2	 <b>VOC:</b> <i>Not covered by the EU limit value (Directive 2004/42/EC). WAX: contains a maximum of 14.7 g/l VOC.</i>
 <b>STORAGE and SHELF LIFE:</b> <i>Can be stored for 2 years between +5°C and +35°C, in its unopened packaging, in a cool and dry place protected from direct sunlight.</i>	

**CONSUMPTION - Single Coat :** *Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.*



1 L covers 25-34 m<sup>2</sup>,  
1 kg covers 25-34 m<sup>2</sup> of area.  
Paint consumption per 1 m<sup>2</sup> surface: 30-40 ml or 30-40 g.

#### APPLICATION AREA

It is applied over decorative materials such as Decostucco.

#### SURFACE PREPARATION

The surface to be applied must be completely dry and free from dirt and dust.

#### SURFACE CONDITIONS

During application and until the products are completely dry, the ambient and surface temperature should be at least +5°C and at most +35°C.

During application, ambient humidity should be below 75%.

The surface moisture content should be below 10%.

#### APPLICATION

Wax should be applied in two (2) coats with a steel trowel onto fully completed Decostucco surfaces without dilution.

Wait 30-60 minutes between coats.

The second coat should be applied before the product is fully dry, followed by polishing with a velvet cloth.

#### HAZARD & PRECAUTIONARY STATEMENTS AND DESCRIPTIONS

H317: May cause an allergic skin reaction.

P261: Avoid breathing dust/fume/gas/mist/vapors/spray.

P333+P313: If skin irritation or rash occurs: Get medical advice/attention.

P362+P364: Take off contaminated clothing and wash it before reuse.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P321: Specific treatment (see label).

P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, please refer to the product's Safety Data Sheet (SDS).

This technical data sheet is prepared based on laboratory data under normal conditions; for any details not sufficiently covered above, please consult technical personnel. Otherwise, the manufacturer cannot be held responsible for errors arising from insufficient information. Our company reserves the right to change this information. If necessary, detailed information regarding the health, safety, and transportation risks and precautions of the products can be found in the Material Safety Data Sheet (MSDS).

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., which holds conformity certificates for ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.