

ALFROYA












Pearlescent Silk Matte Paint

ALFROYA is a decorative paint developed for interior spaces, offering a soft texture and silky matte appearance.



It is easy to apply and allows various patterns and textures to be created effortlessly.

It is water-based, environmentally friendly, and safe for human health.

 CONTENT: <i>Acrylic-based - water-based</i>	 PACKAGING: <i>1 L ; 2,5 L ; 15 L</i>
 THINNING: <i>Ready to use, do not thin.</i>	 DRYING TIME: <i>Drying Time Touch dry (at 23°C): 5-6 hours</i> <small>*drying time may be longer at higher relative humidity and lower temperature.</small>
 PRIMER: <i>San Deco Decoprimer</i>	 Fully Dry: <i>24 hours</i>
 APPLICATION TOOL: <i>Steel trowel</i>	 COLORING: <i>Alfroya Color Chart</i>
 NUMBER of COATS: <i>2</i>	 VOC: <i>Limiting value EU (Directive 2004/42/EC) Category A/I: Decorative effect coatings (water-based): 200 g/L (2010) ALFROYA: contains a maximum of 48 g/L VOC.</i>
 STORAGE and SHELF LIFE: <i>Can be stored unopened for 2 years between +5°C and +35°C in a cool, dry place, protected from direct sunlight.</i>	

CONSUMPTION - Two Coats : *Consumption may vary depending on the type, absorbency, and structure of the surface, as well as application techniques. For precise consumption, a controlled sample application should be performed.*



1 L covers 6,5-8 m²,

1 kg covers 5,3-6,5 m² of area.

Paint consumption for 1 m² of surface is 125-155 ml and 150-190 g.

APPLICATION AREA

It can be used on interior walls, plaster, exposed concrete, and wooden surfaces after proper surface preparation with its own primer.

SURFACE PREPARATION

All kinds of dirt, oil, loose paint, and dust must be cleaned from the surface before application.

Surface defects should be repaired with San Deco Acrylic Putty Fine, followed by priming with San Deco Decoprimer.

SURFACE CONDITIONS

During application and until complete drying, ambient and surface temperatures should be between +5°C and +35°C.

The ambient humidity should be below 75%.

The moisture level of the surface should be below 10%.

APPLICATION

Alfroya should be applied without thinning, after being mixed homogeneously, using a trowel in two (2) coats.

The first coat should be applied smoothly with a trowel.

During the second coat, desired texture and patterns can be achieved by making short circular movements with the trowel.

Allow at least 5-6 hours between coats.

Optionally, different techniques can be developed using a brush instead of a trowel.

For more detailed information, product application videos can be viewed.

If more than one batch number is used within the same project, to prevent batch-based differences, it is recommended to mix the batches proportionally before application.

Local retouching is not recommended. In cases where touch-up is needed, it is advised to reapply the product over the entire damaged area.

HAZARD & PRECAUTIONARY STATEMENTS AND EXPLANATIONS

- H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapors/spray.
P333+P313: If skin irritation or rash occurs: Get medical advice/attention.
P362+P364: Take off contaminated clothing and wash it before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment required (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, please refer to the product's Safety Data Sheet (SDS).

This technical data sheet is prepared based on laboratory data under normal conditions. For details not provided above, please consult technical personnel. Otherwise, errors resulting from insufficient information do not impose any liability on the manufacturer. Our company reserves the right to make changes to this information. For detailed information about health, safety, transport risks, and precautions of the products, please refer to the Material Safety Data Sheet.

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., which holds ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 certification.