

# ATRACTO EXTERIOR

Silky Textured Metallic Pearl Effect Decorative Coating

### 1.PRODUCT DESCRIPTION

It is an acrylic emulsion-based decorative paint containing metallic pigments, featuring a silky texture with gold and silver pearlescent finishes, suitable for exterior surfaces.

## 2. APPLICATION AREA

It is used with a suitable primer on exterior walls, plaster, exposed concrete and wooden surfaces after surface preparation.

#### 3. PRODUCT FEATURES

- Atracto Exterior creates a radiant decorative effect with its metallic pigments.
- Its modified binder and specialized metallic pigments ensure exceptional durability in outdoor conditions.
- The vibrant pigments provide a lasting shine without fading.
- Its high water vapor permeability allows water vapor to be expelled, enabling the surface to breathe.
- Its scented formula enhances the applied area with a pleasant fragrance.
- Water-based, making it environmentally friendly and safe for human health.

## 4. SURFACE PREPARATION

Before application, all dirt, grease, peeling paint, and dust should be removed. Any surface defects should be corrected using SAN DECO ACRYLIC PUTTY EXTERIOR and primed with SAN DECO DECOPRIMER.

### 5. APPLICATION INSTRUCTIONS

## **5.1 Environmental and Surface Conditions**

- During and for 24 hours after the application, it should be ensured that the ambient temperature remains between +5°C minimum and +35°C maximum.
- During the application, it should be ensured that the ambient humidity is below 75%.
- Make sure the humidity value of the application surface is lower than 10%.

## **5.2 Application**

- Atracto Exterior should be mixed homogeneously without diluting and applied in two coats using a trowel.
- For brush and roller applications, it should be diluted with 3-5% water, mixed homogeneously, and applied in two coats.
- A minimum of 6 hours should be waited between coats.
- For more detailed application information, product application videos can be watched.
- When using multiple batches in the same project, they should be mixed in equal proportions to prevent batch variations.
- Touch-ups are not recommended. In case of necessary repairs, the affected wall should be entirely reapplied.



# ATRACTO EXTERIOR

Silky Textured Metallic Pearl Effect Decorative Coating

#### 6. DRYING TIME

The touch dry time at 23°C is 5-6 hours and the complete drying time is 24 hours.

### 7. THEORETICAL CONSUMPTION

- 1 liter of paint covers  $8.0 12.5 \text{ m}^2$ .
- 1 kg of paint covers  $6.5 10.0 \text{ m}^2$ .
- The paint consumption for 1 m<sup>2</sup> is 80-125 ml and 100-150 g.

### 8. STORAGE AND SHELF LIFE

The product can be stored in the original sealed package between +5°C - +35°C temperature for 2 years. Make sure that the product is protected from direct sunlight.

## 9. HAZARD STATEMENTS AND EXPLANATIONS

EU Limit Value (Directive 2004/42/EC)

Category A/l: Decorative effect coatings (water-based): 200 g/l (2010) ATRACTO EXTERIOR PAINT VOC content: Maximum 34.2 g/l

**H317**: May cause an allergic skin reaction.

### 10. PRECAUTIONARY STATEMENTS

**P261:** Avoid breathing dust/fume/gas/mist/vapours/spray.

**P333+P313:** If skin irritation or rash occurs: Get medical advice/attention.

**P362+P364:** Take off contaminated clothing and wash it before reuse.

**P280:** Wear protective gloves/protective clothing/eye protection/face protection.

**P321:** Specific treatment (see...on this label).

**P272:** Contaminated work clothing should not be allowed out of the workplace For more details, refer to the Safety Data Sheet (SDS).

This technical data sheet is prepared based on laboratory data under normal conditions. For additional details, consult technical personnel. The manufacturer is not liable for issues arising from incomplete information. The company reserves the right to modify the data. For detailed information on health, safety, and transportation risks, refer to the Material Safety Data Sheet (MSDS).

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified to TS EN ISO 9001, TS EN ISO 14001, and TS 18001 standards.