

# SANDECO ART EXTERIOR

Metallic Pearl Effect and Quartz Sand Texture Decorative Coating

### 1.PRODUCT DESCRIPTION

SANDECO ART EXTERIOR is an acrylic emulsion-based textured decorative coating, enriched with metallic pigments that create a gold, silver, and pearlescent finish.

### 2. APPLICATION AREA

It is used with a suitable primer on exterior walls, plaster, exposed concrete and wooden surfaces after surface preparation.

### 3. PRODUCT FEATURES

- The organic and inorganic pigments gives a vibrant and textured appearance on the surface.
- Thanks to its metallic pigments and special fillers, it delivers an elegant and decorative finish.
- Its special pigments ensure high UV resistance.
- Its exceptional water vapor permeability promotes the elimination of moisture, allowing the surface to breathe.
- Water-based, making it environmentally friendly and safe for human health.

### 4. SURFACE PREPARATION

After all kinds of dirt, oil, bloated paints, and dust are cleaned from the surfaces, surface defects should be corrected with SAN DECO ACRYLIC PUTTY INTERIOR and primed with SAN DECO DECOPRIMER.

### 5. APPLICATION INSTRUCTIONS

# **5.1 Environmental and Surface Conditions**

- During and for 24 hours after the application, it should be ensured that the ambient temperature remains between +5°C minimum and +35°C maximum.
- During the application, it should be ensured that the ambient humidity is below 75%.
- Make sure the humidity value of the application surface is lower than 10%.

# **5.2 Application**

- After applying the primer, Sandeco Art Exterior is applied in a single coat using a wooden brush, without dilution.
- While the product is still wet, it should be brushed in circular or straight movements to achieve the desired effect.
- For more detailed application guidance, product application videos can be watched.
- When using multiple batches in the same project, they should be mixed in equal proportions to prevent batch-related variations.
- Touch-ups are not recommended. In case of necessary repairs, the entire affected wall should be reapplied.



# SANDECO ART EXTERIOR

Metallic Pearl Effect and Quartz Sand Texture Decorative Coating

### 6. DRYING TIME

The touch dry time at 23°C is 4-5 hours and the complete drying time is 20-24 hours.

### 7. THEORETICAL CONSUMPTION

Depending on surface smoothness, porosity, and application method, for a single coat application:

- 1 liter covers  $6.5 8.5 \text{ m}^2$ .
- 1 kg covers  $5.0 6.5 \text{ m}^2$ .
- Paint consumption per 1  $m^2$  area is between 120 160 ml and 150 200 g.

### 8. STORAGE AND SHELF LIFE

The product can be stored in the original sealed package between +5°C/+35°C temperature for 2 years. Make sure that the product is protected from direct sunlight.

### 9. HAZARD STATEMENTS AND EXPLANATIONS

EU Limit Value (Directive 2004/42/EC)

Category A/I: Decorative effect coatings (water-based): 200 g/I (2010)

SANDECO ART EXTERIOR VOC content: Maximum 42.5 g/l

H317: May cause an allergic skin reaction.

# 10. PRECAUTIONARY STATEMENTS

**P261:** Avoid breathing dust/fume/gas/mist/vapours/spray.

**P333+P313:** If skin irritation or rash occurs: Get medical advice/attention.

P362+P364: Take off contaminated clothing and wash it before reuse.

**P280:** Wear protective gloves/protective clothing/eye protection/face protection.

**P321:** Specific treatment (see...on this label).

**P272:** Contaminated work clothing should not be allowed out of the workplace

# **Note:**

For more details, refer to the **Safety Data Sheet (SDS)**.

This technical data sheet is prepared based on laboratory data under normal conditions. For further details, consult technical personnel. The manufacturer is not responsible for errors resulting from incomplete information. The company reserves the right to modify the data. For comprehensive information on health, safety, and transportation risks, refer to the **Material Safety Data Sheet (MSDS)**.

This product is manufactured by **Deka Boya Sanayi ve Tic. A.Ş.**, certified to **TS EN ISO 9001, TS EN ISO 14001, and TS 18001 standards**.